



Kansas City:
 8341 Ruby Ave.
 Kansas City, KS 66111
913-766-7200
 855-818-4958 toll-free
 913-766-7201 fax

Tulsa:
 131 S. 147th E. Ave.
 Tulsa, OK 74116
918-641-0641
 866-674-7657 toll-free
 918-641-0640 fax



contact@metalpanelsinc.com
 www.metalpanelsinc.com

PVDF COLOR SELECTION

REGAL WHITE SR .68 SRI 82	SNOW WHITE SR .63 SRI 75	ALMOND SR .60 SRI 70	SANDSTONE SR .54 SRI 63	ASH GRAY SR .39 SRI 41
TUNDRA SR .34 SRI 35	SLATE GRAY SR .42 SRI 47	CHARCOAL SR .32 SRI 32	BROWNSTONE SR .38 SRI 40	SURREY BEIGE SR .40 SRI 43
COLONIAL RED SR .33 SRI 34	REGAL RED SR .42 SRI 45	MEDIUM BRONZE SR .30 SRI 31	DARK BRONZE SR .26 SRI 24	PATRICIAN BRONZE SR .27 SRI 26
MANSARD BROWN SR .30 SRI 30	PATINA GREEN SR .46 SRI 51	EVERGREEN SR .26 SRI 24	CLASSIC GREEN SR .28 SRI 27	MATTE BLACK SR .27 SRI 26
ROMAN BLUE SR .26 SRI 24	REGAL BLUE SR .26 SRI 24	BRANDYWINE SR .26 SRI 24		

STANDARD COLORS:
 REGAL WHITE
 SANDSTONE
 SLATE GRAY
 CHARCOAL GRAY
 SURREY BEIGE
 MEDIUM BRONZE
 DARK BRONZE
 MANSARD BROWN
 EVERGREEN
 MATTE BLACK

METALLIC COLORS

SILVER METALLIC SR .58 SRI 66	CHAMPAGNE SR .38 SRI 38	COPPER METALLIC SR .45 SRI 50	PRE-WEATHER GALVALUME SR .30 SRI 27

- Final color selection should be made from actual color chips.
- Visit www.metalpanelsinc.com for the most current information.
- A 40-year limited paint warranty is available for all colors upon written request. Please inquire. (Outside the continental US, please inquire.)
- Solar Reflectivity (SR): Solar reflectivity or reflectance is the measure of a material's ability to reflect solar energy or sunlight from its surface. SR values are numbered 0 to 1.0. A value of 0 indicates that the surface absorbs all solar energy, and a value of 1.0 indicates total reflectance. ENERGY STAR requires an SR value of 0.25 or higher for steep slope roofing (above 2:12) and an SR value of 0.65 or higher for low slope roofing (2:12 or less). For more information, please visit www.energystar.gov.
- Solar Reflectance Index (SRI): The SRI is used to determine compliance with LEED requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. To meet LEED requirements, a roofing material must have an SRI of 29 or greater for steep slope roofing and an SRI value of 78 or higher for low slope roofing. For more information, visit www.usgbc.org.